

ITG  
A B S T R A C T O F T H E D I S C L O S U R E

A polyolefin article is provided which exhibits excellent levels of mechanical strength and dimensional stability to temperature while not incorporating a dissimilar reinforcing material, such as a glass fiber, and which can be readily manufactured. Methods for manufacture of the polyolefin article are also provided.

09355946-081695  
The polyolefin article being composed of polyolefin and including an oriented polyolefin material to maintain its average coefficient of linear expansion at a value of not exceeding  $5 \times 10^{-5}$  ( $^{\circ}\text{C}$ ) in the  $20 - 80^{\circ}\text{C}$  range, and the method for manufacture of the polyolefin article including the steps of depositing, on a surface of an oriented polyolefin material having a value of not exceeding  $5 \times 10^{-5}$  ( $^{\circ}\text{C}$ ) for average coefficient of linear expansion in the  $20 - 80^{\circ}\text{C}$  <sup>RS-66</sup> a low-molecular compound capable of dissolving the polyolefin, and thereafter effecting bonding of the oriented polyolefin material by the application of pressure and heat.